Semiannual Subcontract Report 1 April 1993 – 30 September 1993

T. Jester Siemens Solar Industries Camarillo, California

NREL technical monitor: R. Mitchell



National Renewable Energy Laboratory 1617 Cole Boulevard Golden, Colorado 80401-3393 A national laboratory of the U.S. Department of Energy Operated by Midwest Research Institute for the U.S. Department of Energy under contract No. DE-AC02-83CH10093

Prepared under Subcontract No. ZM-2-11040-1

June 1994



DISTRUCTION OF TI-HE DOCUMENT IS UNLIMITED

NOTICE

NOTICE: This report was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or any agency thereof.

> Printed in the United States of America Available from: National Technical Information Service U.S. Department of Commerce 5285 Port Royal Road Springfield, VA 22161

Price: Microfiche A01 Printed Copy A03

Codes are used for pricing all publications. The code is determined by the number of pages in the publication. Information pertaining to the pricing codes can be found in the current issue of the following publications which are generally available in most libraries: *Energy Research Abstracts (ERA)*; *Government Reports Announcements and Index (GRA and I)*; *Scientific and Technical Abstract Reports (STAR)*; and publication NTIS-PR-360 available from NTIS at the above address.



DISCLAIMER

Portions of this document may be illegible electronic image products. Images are produced from the best available original document.

PREFACE

Siemens Solar Industries (SSI) began a three-year, three-phase cost shared contract in March 1992 to demonstrate significant cost reductions and improvements in manufacturing technology. The work has focused on near-term projects for implementation in the SSI Czochralski (Cz) manufacturing facility in Camarillo, California.

The work has been undertaken to increase the commercial viability and volume of photovoltaic manufacturing by evaluating the most significant cost categories and then lowering the cost of each item through experimentation, materials refinement, and better industrial engineering.

The initial phase of the program has concentrated in the areas of crystal growth, wafer technology and environmental, safety and health issues.

Significant contributions have been made by the key personnel involved in the program. They include Jerry Anderson in module and cell evaluations, Kim Mitchell, David Tanner and Karen Pauls in the crystal growth and wafer areas, and Sergio Vasquez in the environmental, safety and health area.

SUMMARY

OBJECTIVES

The objective of the program at Siemens Solar is to reduce costs in photovoltaic manufacturing by approximately 10% per year. The specific milestones are shown in Table 1. which consists of three focused tasks relating to cost reduction, the wafer, cell and module tasks. The silicon wafer itself contributes about half of the total cost and has the most potential for cost improvement. The cell processing costs are about a quarter of the total costs, with cell efficiency and yield results being most important. Module assembly and packaging costs are the balance, with the module design, both materials and labor, contributing significantly.

	Phase 1	Phase 2	Phase 3
Task 1. Silicon Crystal Growth & Thin Wafer Technology			
A. Increase Cz grower productivity by 25%	10%	15%	25%
 B. Demonstrate utility of prototype wire saw Deliver 100 wire sawn wafers 	•		
C. Demonstrate 0.010"-thick wire sawn wafers Deliver 100 0.010" wafers		•	
D. Reduce wafer cost by 30%		15%	30%
Task 2. Silicon Cell Processing Reduce cell cost by 30% (\$/watt)	10%	20%	30%
Task 3. Silicon Module Fabrication & Environmental, Safety & Health Issues			
 Reduce module fabrication costs by 35% Deliver modules demonstrating reduced \$/watt 	10%	25% 2 modules (20%)	35% 6 modules (25%)
B. Reduce caustic use and waste	Define process and equipment	10% reduction	35% reduction
C. Replace CFC's	Evaluate CFC alternatives		90% reduction in CFC usage

Table 1. Cz manufacturing technology milestones.

Task 1: Silicon Crystal Growth and Thin Wafer Technology. Crystal growing costs are driven by material growing yields and indirect manufacturing costs such as electricity and machine parts used each time an ingot is fabricated. Wafering costs are driven by labor and the number of good slices yielded per length of crystal processed.

The second year of the contract has focused on throughput of the crystal growing machines. This has been done by using larger diameter crucibles and higher speed growth techniques, and with the implementation of wire saw machines in production to improve the yielded wafers per inch of ingot.

Task 2: Silicon Cell Processing. Cell processing costs are driven by the electrical contacts used, and the labor required for the process steps to clean the wafer, form the semiconductor junction, and apply the contacts.

The second task has been focused on the improvement of the contacting system through experimentation with various contacting pastes, and the automation of handling operations in the cell fabrication process.

Task 3: Silicon Module Fabrication and Environmental, Safety, and Health Issues. Module costs are highly sensitive to labor and materials. The module design tasks are driven by high reliability in the field and lower costs. Included in this task is the environmental work to eliminate chlorofluorocarbon (CFC) usage and significantly reduce the caustic waste volumes.

This year SSI has focused on lower module costs and the complete elimination of CFC usage in the manufacturing processes.

DISCUSSION AND CONCLUSIONS

During this six-month period (March 13, 1993 through September 30, 1993), several significant manufacturing technology improvements were achieved.

The crystal growing operation improved significantly with an increase in growth capacity. Higher growing throughput has been demonstrated with larger crucibles, higher polysilicon packing density, and higher pull speeds. Approximately 30% of the crystal growing machines have been converted to this new method.

Wafer processing with wire saws progressed rapidly and the operation is completely converted to wire saw wafer processing. The wire saws have proven to yield over 40% more wafers per inch in production. The capacity improvement generated by wire saws has increased overall manufacturing volume by over 40% without any additional expenses in crystal growth. The use of wire saws has made the crystal growth process much more effective by this higher throughput for a given amount of ingot. Wire saw yields progressed from 70% to over 90% in the time period reported.

Semiannual Report April - October 1993

This improvement is credited to better understanding of and experimentation with the raw materials feeding the process, specifically the wire, oil and Silicon Carbide, and with experimentation on number of runs per batch of slurry cutting media.

Cell processing improvements have focused on better understanding of the contact paste and firing processes. The work with Ferro Corporation has been on-going, with experimental pastes being run periodically. To date, the control samples using the standard production pastes are still the best performers. The cell electrical distribution improved over this period of time by approximately 3%.

Module designs for lower material and labor costs have begun with the focus on a new junction box, larger modules with larger cells, and less costly framing technique. CFC usage has been completely eliminated in the SSI manufacturing facility during this phase of the contract. Two modules demonstrating these cost reductions have been delivered during this phase, meeting the contract deliverables.

The contract performance to date is shown in Table 1.

Category	% Reduction in Cost	
 Crystal Growth/Thin Wafers 43 vs. 29 wafers/inch 	2%	
2. Larger Cell/Module	16%	
3. New J-box	2%	
Total	20%	

Table 1. Cost Reduction Summary for Phase II

Semiannual Report April - October 1993

:

CONTENTS

1.0	Crystal Growth and Thin Wafer Technology	1
	1.1 Machine Hardware1.2 Larger Ingot1.3 Wire Saw Implementation	1 1 3
2.0	Cell Processing	5
	 2.1 Cell Performance	5 6 7
3.0	Module Fabrication and Environmental, Safety and Health Issues	8
	 3.1 75 Watt Module	8 10 12 13

Figures

1-1.	Drawing of large diameter ingot 2
1-2.	Wire saw vs. ID saw comparison
1-3.	Wire saw yields 4
2-1.	Electrical distribution improvement
2-2.	Contact paste comparison study 6
2-3.	Flowchart showing automated cell process flow
3-1.	I-V curve for 75 and 53 Watt modules 9
3-2.	75 Watt modules drawings
3-3.	New j-box design
3-4.	Layout of the semi-automated assembly line
3-5.	Caustic waste reduction process flow

SECTION 1.0 CRYSTAL GROWTH AND THIN WAFER TECHNOLOGY

The Crystal Growth and Thin Wafer Technology task under this phase of the contract is focused on three areas: machine hardware improvements for the existing Czochralski (Cz) crystal growers in use at Siemens Solar Industries (SSI), the growth of larger diameter ingots, and the implementation of wire saw slicing machines.

1.1 MACHINE HARDWARE

The graphite redesign work done during the previous year of the program (year 1) which demonstrated an annual cost savings of over \$300,000 was verified this year. The lifetime of graphite parts has increased substantially. Typical graphite susceptor usage has gone from 5.2 runs to over 16 runs prior to replacing.

Additional focus on throughput has initiated the use of larger diameter crucibles in the existing crystal growers. Initial pilot runs were conducted with no disruption to the production process, and with comparable growth yields. The larger crucibles have demonstrated over 10% improvement in kg/day grown, with virtually no cost addition. This improvement has been implemented in 30% of the production growers to date.

1.2 LARGER DIAMETER INGOTS

A significant cost reduction in the total module cost is realized by making larger modules, with larger cells. The development program at SSI under this phase of the contract has focused on this larger cell and larger module.

Larger diameter ingots have been grown in order to increase cell size by 35%. A slightly larger diameter ingot of nominal 5.5" is being grown which has resulted in a 6% increase in ingot cross sectional area. This 6% ingot cross section area increase is a direct improvement in production volume, for no additional cost. A diagram of the new larger ingot is shown in Figure 1-1. This change also included a new ingot shape to maximize the area of the cell from the grown ingot. An analysis of the subsequent processes in the production facility showed that a small flat area is required for machines which align mechanically to the wafer. With the diameter tolerance on as grown ingot being considered, the shape shown in Figure 1-1. with 125 mm flats was designed. This new ingot produces a cell with 35% more active area with reference to the standard 4.05" square cell. This change in production posed no significant problems.

- --

Semiannual Report April - October 1993

÷



Fig. 1-1. Larger Diameter Ingot

Semiannual Report April - October 1993

.

1.3 WIRE SAW IMPLEMENTATION

Wire saw implementation was the focus for wafer fabrication during this phase of the contract. Complete conversion from Inner Diameter (ID) saws to wire saws was accomplished during this phase .

Wafer yield per inch has improved substantially with this change over. In addition to less material lost with each slice, the ability to slice thinner wafers has had a substantial impact. Wafer thickness has decreased by 40% with wire saws; from .021" thick as sliced with ID saws to .013" thick with wire saws. Wafer yield has improved from 29 wafers per inch of ingot with ID saws to over 43 wafers per inch with wire saws. Figure 1-2 shows this improvement in yielded wafers per inch.

Slicing the larger diameter ingot discussed in section 1.2. posed no significant issues for wire sawing.



Figure 1-2. Wafers per inch, ID saws compared to Wire Saws.

Semiannual Report April - October 1993

Wire saw mechanical yields also improved over this reporting period. Figure 1-3. shows the mechanical improvement seen over the last year, with significant events noted on the chart. The major improvement for 80% yield to 90% in recent months has been a result of the improvement in material quality characteristics of the oil and the wire. The wire must be defect free, and the oil viscosity must be tightly controlled, to achieve greater than 90% mechanical yield.



Fig. 1-3. Wire Saw yield improvement.

2

SECTION 2.0 CELL PROCESSING

The cell processing task of this contract has focused on three items during this phase: increasing average cell performance, contact paste studies, and automated handling equipment for cell processing.

2.1 CELL PERFORMANCE

Improvement in the cell distribution has been consistent throughout this program. Figure 2-1. shows the electrical test amperage improvement comparing initial distribution in 1992, and the comparable time frame for 1993. This electrical improvement is credited to better process control in the diffusion area, new equipment for the anti-reflective coating process, and an additional etch step that has been added to the process. This was discussed in more detail in the annual report for Phase I. Additional increases are expected, as process control is improved in the production line.



Fig.2-1. Cell electrical performance improvement.

Semiannual Report April - October 1993

2.2 CONTACT PASTE STUDIES

A paste study conducted with Ferro Corporation to improve the electrical contacting of cells was performed in which the standard paste formulation was modified in an effort to reduce both the contact resistance to the cell and the linear resistance of the grid lines. The standard paste used in production continues to be the best performer in all categories of electrical amps produced and lowest contact and line resistances. Figure 2-2. (a-c) shows the contact paste comparison study results. More work is planned with Ferro.



a. Electrical performance of cells with various pastes



b. Contact resistance

c. Line resistance



÷

2.3 AUTOMATED CELL PROCESSING

Automated handling systems have been designed and installed in the cell fabrication area during this phase of the contract. The result has been the reduction of over 50% of the labor required in this portion of the cell process. The automated handling system begins with the anti-reflective coating process and ends with a tested cell. The transfer points are a combination robot, and pick and place mechanism system. A flowchart of the process is shown in Figure 2-3. in which the solar cells are automatically machine handled throughout this area of the production facility. The automated equipment was designed to handle both the 4.05" square cell and the 125 mm semi-round cell discussed in section 1.2.



Fig. 2-3. Flowchart showing automated cell processing.

Semiannual Report April - October 1993

SECTION 3.0 MODULE FABRICATION AND ENVIRONMENTAL, SAFETY AND HEALTH ISSUES

A majority of the module finishing costs in photovoltaics are in the materials and labor used for fabricating the modules. The requirement of reliability has driven the industry to standardize the laminate design to include glass, EVA, and various back sheet materials which provide an electrically insulating, environmentally resistant package. In working through the opportunity to reduce costs in the module design, three things became apparent during this phase of the contract: the module size has a significant impact on the dollar per watt material cost, the laminate construction is the significant contributor to the labor component of the costs, and the framing and junction box are major material contributors. During this phase of the contract, all three have been addressed.

3.1 75 WATT MODULE DESIGN

To address the larger module and it's affect on reducing the dollar per watt, a larger ingot which could be grown easily in the facility was chosen. The starting design assumptions were to maximize the amount of power in a given module unit. Coupling this assumption with the ingot design, gave a cell area which is 35% larger than the 4.05" square cell. This cell power is further enhanced by the white area of the laminate using larger spacing of the cells. Modules made from thirty six cells in series produce 75 Watts in this new module design. The IV curves for the 75 Watt module are shown in Figure 3.1 a. along with the standard M55 curve in Figure 3.1 b.

Other significant design changesconsidered were the framing technique and electrical termination used. Two modules were designed, one with the standard aluminum frame and a large junction box, and one with a plastic frame and a two conductor cable assembly. In the final cost summary, the two module techniques were similar in dollar per watt, where the savings of the plastic frame were offset by the labor and expense of the cable assembly technique. The significant cost reduction is mainly due to the larger amount of watts (75 vs. 53) being framed and terminated. The two 75 Watt module designs are shown in Figure 3.2.

÷



Fig. 3-1 a. I-V characteristics for a 75 Watt module.



Semiannual Report April - October 1993

-



-

Fig. 3-2. 75 Watt module designs.

Semiannual Report April - October 1993

.

3.2 NEW JUNCTION BOX

A new junction box has been designed which combines the benefit of the wire termination and the large junction box. A cost reduction benefit of over 2% is expected in production. The new junction box allows for wire connections and conduit type fitting connections. The installation of this new design on the module during manufacturing has also been considered, with an open area for laminate ribbon to feed through for electrical connection and larger area contact for gluing to the module back surface. The new design is shown in Figure 3.3. This junction box will be Underwriters Laboratory approved prior to production implementation.





Fig. 3-3. New j-box design

Semiannual Report April - October 1993

3.3 SEMI-AUTOMATED ASSEMBLY LINE

A design for a semi-automated assembly line for 75 Watt laminate manufacturing has been finished during this phase. The design is a flexible material movement system which relies on fixtures which travel along a track system. The operators of the system place cells on the fixtures which move down the line for final solder connections and laminate lay-up. This design will allow for a 30% reduction in the amount of labor required for assembling 75 Watt laminates. An additional requirement of ergonomic comfort has been included in this design. The system layout is shown in Fig. 3-4.



Fig. 3-4. Layout of semi-automated assembly line.

3.4 ENVIRONMENTAL, SAFETY & HEALTH

For the Module Fabrication and Environmental, Safety and Health Issues task, the focus during this reporting period was the complete elimination of CFC usage in the manufacturing process, and the reduction in the amount of caustic waste produced.

CFC usage was discontinued during May of this year by the implementation of a noclean flux solder paste. The development of the use of this paste was done during the last phase of the contract (Phase 1), with the implementation of its use this year. Complete elimination of CFC use has been accomplished, one and a half years ahead of the contract schedule.

The second focus on reducing caustic waste has been attacked using two methods. The first method is the reduction of waste created per cell processed. This has been accomplished mainly with the use of wire sawn wafers which require less etching to remove saw damage. This reduction in caustic waste per wafer is over 10% for the reporting period of this contract. The second method of reducing the caustic waste leaving the facility has been to look at processing techniques to eliminate the water in the caustic waste stream. One such proposal is shown in Figure 3-5. Several proposals have been solicited, with this the most promising. Many other factors must be considered prior to any treatment of waste, for example the safety issues of the system, the local regulatory permits required, and the cost of the hardware. These considerations will be examined during the balance of the contract.



Fig. 3-5. Caustic waste reduction process flow

REPORT DOCUMENTATION PAGE

Form Approved OMB NO. 0704-0188

REPORT DOCUMENTATION PAGE			OMB NO. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.					
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE May 1994	 REPORT TYPE AND DATES COVERED Semiannual Subcontract Report - 1 April 1993 - 30 September 1993 			
4. TITLE AND SUBTITLE			5. FUNDING NUMBERS		
PV Cz Silicon Manufacturing Te	chnology Improvements		C: ZM-2-11040-1		
6. AUTHOR(S)			TA: PV450101		
T. Jester					
7. PERFORMING ORGANIZATION NAM	E(S) AND ADDRESS(ES)		8. PERFORMING ORGANIZATION		
Siemens Solar Industries 4650 Adohr Lane Camarillo, California 93012	REPORT NUMBER				
9. SPONSORING/MONITORING AGEN	CY NAME(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
National Renewable Energy Lat	poratory		TP-411-6634		
Golden, CO 80401-3393					
			DE94011818		
11. SUPPLEMENTARY NOTES	Aitoball				
12a. DISTRIBUTION/AVAILABILITY ST	ATEMENT		12b. DISTRIBUTION CODE		
		110-270			
			00-210		
13. ABSTRACT (Maximum 200 words)					
This report describes work per manufacturing technology. The Czochralski (Cz) manufacturing of photovoltaic manufacturing experimentation, materials refi improvements were achieved. throughput was demonstrated completely converted to wire-se improvement generated by wire cyrstal growth. (3) Cell process Module designs for lower mater less costly framing technique. contract.	formed under a 3-year contract to e work focused on near-term pro- g facility in Camarillo, California, by evaluating the most significant nement, and better industrial eng (1) The crystal-growing operatio with larger crucibles, higher poly- saw wafer processing. The wire s re saws increased overall manufa ssing improvements focused on b erial and labor costs began with t CFC usage was completely elim	o demonstrate significant cost red jects for implementation in the Sig and was undertaken to increase t a cost categories and then lowerin ineering. During this reporting per n improved with an increase in gr silicon packing density, and highe saws yield over 40% more wafers acturing volume by more than 40% better understanding of the contac he focus on a new junction box, la innated in the SSI manufacturing f	uctions and improvements in emens Solar Industries (SSI) he commercial viability and volume g the cost of each item through riod, several significant owth capacity. Higher growing r pull speeds. (2) The operation was per inch in production. The capacity without additional expenses in t paste and firing processes. (4) arger modules with larger cells, and acility during this phase of the		
14. SUBJECT TERMS			15. NUMBER OF PAGES		
Czochraiski ; silicon ; manutacturing ; photovoltaics ; solar cells			16. PRICE CODE A03		
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT		

...